



Warrington Certification Ltd
 Holmesfield Road
 Warrington
 WA1 2DS
 United Kingdom

T : +44 (0) 1925 646 669
 W: www.warringtoncertification.com
 E: etass@exova.com



Member of
www.eota.eu

European Technical Assessment

ETA 14/0381 of 7/10/14

Technical Assessment Body issuing the ETA and designated according to Article 29 of the Regulation (EU) No 305/2011:	
Trade name of the construction product	fischer FiGM PFS+ intumescent Graphite Mastic
Product family to which the construction product belongs	Fire Stopping and Sealing Product Penetration Seals
Manufacturer	Fischerwerke GmbH & Co Weinhalde 14-18 72178 Waldachtal Germany
Manufacturing plant(s)	E/091
This European Technical Assessment contains	16 pages including 3 Annex(es) which form an integral part of this assessment.
	Annex(es) A - C Contain(s) confidential information and is/are not included in the European Technical Assessment when that assessment is publicly available.
This European Technical Assessment is issued in accordance with regulation (EU) No 305/2011, on the basis of	ETAG 026, edition 2011, used as European Assessment Document (EAD)

General Comments

1. This European Technical Assessment is issued by Warrington Certification Limited on the basis of ETAG 026 Fire Protective Products Part 1: General June 2013, and Part 2: Fire Stopping and Fire Sealing Products Aug 2011, Used as European Assessment Document.
2. This European Technical Assessment is not to be transferred to manufacturers or agents of manufacturers other than those indicated on page 1, or manufacturing plants other than those indicated on page 1.



1 SPECIFIC CONDITIONS OF THE EUROPEAN TECHNICAL ASSESSMENT

1 Technical Description of the Product

(Detailed information and data are given in Annexes)

- 1) fischer FiGM PFS+ Intumescent Mastic is an acrylic based graphite sealant used to reinstate the fire resistance performance of wall constructions where they have been provided with apertures for the penetration of single or multiple services.
- 2) fischer FiGM PFS+ Intumescent Mastic is gun applied to annular space around the service(s) to the required depth (for details see Annex C)
- 3) fischer FiGM PFS+ Intumescent Mastic is supplied in 310ml cartridges and 5Kg & 10 Kg Pails.

Internal use- ETAG 026-2 (used as European Assessment Document EAD) Type Z₁.

2 Specification Of The Intended Use In Accordance With The Relevant EAD

2.1 Intended Use

The intended use of fischer FiGM PFS+ Intumescent Mastic is to reinstate the fire resistance performance of rigid and flexible wall constructions where they are penetrated by various cables, plastic and insulated metallic pipes

- 1) The specific elements of construction that the system fischer FiGM PFS+ Intumescent Mastic may be used to provide a penetration seal in, are as follows:

Rigid walls: The wall must have a minimum thickness of 100 mm and comprise concrete, aerated concrete or masonry, with a minimum density of 650 kg/m³.

Rigid walls: The wall must have a minimum thickness of 120 mm and comprise concrete, aerated concrete or masonry, with a minimum density of 650 kg/m³.

Flexible walls The wall must have a minimum thickness of 100 mm and comprise timber or steel studs lined on both faces with minimum 2 layers of 12.5 mm thick, 'Type F' Gypsum boards according to EN 520. In timber stud walls, no part of the penetration shall be closer than 100 mm to a stud, the cavity must be closed between the penetration seal and the stud and minimum 100 mm of insulation of class A1 or A2 according to EN 13501-1, is provided within the cavity between the penetration seal and the stud.

Flexible walls The wall must have a minimum thickness of 120 mm and comprise timber or steel studs lined on both faces with minimum 2 layers of 15 mm thick, 'Type F' Gypsum boards according to EN 520. In timber stud walls, no part of the penetration shall be closer than 100 mm to a stud, the cavity must be closed between the penetration seal and the stud and minimum 100 mm of insulation of class A1 or A2 according to EN 13501-1, is provided within the cavity between the penetration seal and the stud.

The supporting construction must be classified in accordance with EN 13501-2 for the required fire resistance period.



- 2) The fischer FiGM PFS+ Intumescent Mastic may be used to provide a penetration seal with plastic and insulated metallic pipes, and cables (for details see Annex C).
- 3) The total amount of cross sections of services (including insulation) should not exceed 60% of the penetration area.
- 4) The system fischer FiGM PFS+ Intumescent Mastic may be used to seal apertures in the separating element up to 100mm wide by 300mm high. The minimum permitted separation between adjacent seals/apertures is 200mm.
- 5) Pipes must be installed singular, cables require no minimum separation.
- 6) Services in walls shall be supported at maximum 270mm from the face of the separating element.
- 7) The provisions made in this European Technical Assessment are based on an assumed working life of the fischer FiGM PFS+ Intumescent Mastic of 10 years, provided that the conditions laid down in the product data sheet for the packaging/transport/storage/installation/use/repair are met. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

2.2 Use Category

Type Z₁: Intended for use in internal conditions with humidity equal to or higher than 85% RH excluding temperatures below 0°C, without exposure to rain or UV.



3 Performance Of The Product And References To The Methods Used For Its Assessment

The assessment of fitness for use has been made in accordance with EOTA ETAG 026 Part 2: 2011-08-08 (used as European Assessment Document, EAD)

ETAG Clause No.	ETA Clause No.	Characteristic	Assessment of characteristic
		Mechanical resistance and stability	Not relevant
		Safety in case of fire	See Clause 3.1
2.4.1	3.1	Reaction to fire	Class F according to EN 13501-1
2.4.2	3.2	Resistance to fire	See clause 3.2 & Annex C
		Hygiene, Health and the Environment	
2.4.3	3.3	Air permeability	See clause 3.3
2.4.4	3.4	Water permeability	No performance determined
2.4.5	3.5	Dangerous substances	See clause 3.5
		Safety in use	
2.4.6	3.6	Mechanical resistance and stability	No performance determined
2.4.7	3.7	Resistance to impact/movement	No performance determined
2.4.8	3.8	Adhesion	No performance determined
		Protection against noise	No performance determined
2.4.9	3.9	Airborne sound insulation	No performance determined
		Energy, Economy and Heat Retention	
2.4.10	3.10	Thermal properties	No performance determined
2.4.11	3.11	Water vapour permeability	No performance determined
		General aspects relating to fitness for use	
2.4.12	3.12	Durability and serviceability	Z₁

3.1 Reaction to fire

System fischer FIGM PFS+ Intumescent Mastic is classified '**F**' in accordance with EN 13501-1.

3.2 Resistance to fire

System fischer FIGM PFS+ Intumescent Mastic has been tested in accordance with BS EN 1366-3: 2009 based upon the test results and the field of direct application specified within EN 1366-3: 2009, the fischer FIGM PFS+ Intumescent Mastic has been classified in accordance with EN 13501-2, as given in Annex C:



The seals may only be penetrated by the services described in Annex C; other parts or support constructions must not penetrate the seal.

The service support construction must be fixed to the building element containing the penetration seal or a suitable adjacent building element, in such a manner that in the case of fire, no additional load is imposed on the seal. Furthermore it is assumed that the unexposed face support is maintained for the required period of fire resistance.

Pipes must be perpendicular to the seal surface.

It is assumed that compressed air systems are switched off by other means in the case of fire.

The function of the pipe seal in case of pneumatic dispatch systems, pressurised air systems etc. is guaranteed only when the systems are shut off in case of fire.

The assessment does not cover the avoidance of destruction of the seal or of the abutting building element(s) by forces caused by temperature changes in case of fire. This has to be considered when designing the piping system.

The approval does not address any risks associated with leakage of dangerous liquids or gases caused by failure of the pipe(s) in case of fire.

The durability assessment does not take account of the possible effect of substances permeating through the pipe on the penetration seal.

3.3 Air permeability

System fischer FiGM PFS+ Intumescent Mastic has been tested in accordance with BS EN 1314-1 to provide the following results:

Product tested				
Pressure (Pa)	Results under positive chamber pressure		Results under negative chamber pressure	
	Leakage (m ³ /h)	Leakage (m ³ /m ² /h)	Leakage (m ³ /h)	Leakage (m ³ /m ² /h)
50	0.2	5.6	0.3	8.3
100	0.4	11.1	0.6	16.7
150	0.7	19.4	0.9	25.0
200	1.0	27.8	1.2	33.3
250	1.1	30.6	1.6	44.4
300	1.2	33.3	1.9	52.8
450	2.2	61.1	2.7	75.0
600	2.4	66.7	3.4	94.4



3.4 Water permeability

No performance determined

3.5 Dangerous substances

Fischerwerke GmbH & Co is required to submit a written declaration stating whether or not the fire stopping and fire sealing product contains dangerous substances according to European and national regulations, when and where relevant in the Member States of destination, and shall list these substances.

Fischerwerke GmbH & Co declare that Product fischer FiGM PFS+ Intumescent Mastic is in compliance with Council Directive 76/769/EEC of 27th July 1976 on the approximation of the laws, regulations and administrative provisions of the Member States relating to restrictions on the marketing and use of certain dangerous substances and preparations (incl. all amendments and adaptations).

Confirmation has further been declared that all dangerous chemical substances ≥ 1.0 % w/w as well as all toxic, carcinogenic, toxic for reproduction and mutagenic chemical substances ≥ 0.1 % w/w (Status: 29. adaption – 2004/73/EG – of the EU directive 67/548/EEC - classification, packaging and labelling of dangerous substances) are stated in the fischer FiGM PFS+ Intumescent Mastic material safety data sheets (according to 91/155/EEC including amendments) and have been considered for the classification of the products according to the directive 1999/45/EG (classification of preparations, including amendments).amendments).

All dangerous chemical substances are below the classification limits of 67/548/EEC

3.6 Mechanical resistance and stability

No performance determined.

3.7 Resistance to impact/movement

No performance determined.

3.8 Adhesion

Not relevant.

3.9 Airborne sound insulation

No performance determined.

3.10 Thermal Properties

No performance determined.

3.11 Water vapour permeability

No performance determined.



3.12 Durability and serviceability

fischer FiGM PFS+ Intumescent Mastic has been tested in accordance with EOTA Technical Report - TR024 – Edition November 2006, for the type Z₁ use category specified in ETAG 026-3 (used as European Assessment Document, EAD), and the results of the tests have demonstrated suitability for penetration seals intended for use in internal conditions with humidity equal to or higher than 85% RH excluding temperatures below 0°C, without exposure to rain or UV.

4 Assessment And Verification Of Constancy Of Performance (Hereinafter AVCP) System Applied, With References To Its Legal base

According to the decision 1999/454/EC of the European Commission the system of assessment and verification of constancy of performance (see Annex V to the Regulation (EU) No 305/2011) given in the following table apply:

Products	Intended uses	Level or Class	System
Fire stopping and fire sealing products	For fire compartmentation and / or fire protection or fire performance	Any	System 1

5. Technical Details Necessary For The Implementation Of The AVCP System, As Provided For In The Applicable EAD.

Tasks for the Manufacturer

Factory production control

The manufacturer shall exercise permanent internal control of production. All the elements, requirements and provisions adopted by the manufacturer shall be documented in a systematic manner in the form of written policies and procedures, including records of results performed. This production control system shall ensure that the product is in conformity with this European technical assessment.

The manufacturer may only use constituent materials stated in the technical documentation of this European technical assessment.

The factory production control shall be in accordance with the Control Plan of 11.2.14 relating to the European technical assessment ETA 14/0381 which is part of the technical documentation of this European technical assessment. The "Control Plan" is laid down in the context of the factory production control system operated by the manufacturer and deposited at Warrington Certification Limited.

The results of factory production control shall be recorded and evaluated in accordance with the provisions of the Control Plan.



Other tasks of manufacturer

Additional information

The manufacturer shall provide a technical data sheet and an installation instruction with the following minimum information:

(a) Technical data sheet:

- Field of application:
- Building elements for which the penetration seal is suitable, type and properties of the building elements like minimum thickness, density, and - in case of lightweight constructions – the construction requirements.
- Services for which the penetration seal is suitable, type and properties of the services like material, diameter, thickness etc. in case of pipes including insulation materials; necessary/allowed supports/fixings (e.g. cable trays)
- Limits in size, minimum thickness etc. of the penetration seal
- Construction of the penetration seal including the necessary components and additional products (e.g. backfilling material) with clear indication whether they are generic or specific.

(b) Installation instruction:

- Steps to be followed
- Procedure in case of retrofitting.

Tasks of approved bodies

The approved body shall perform the

- initial type-testing of the product,
- initial inspection of factory and of factory production control,
- continuous surveillance, assessment and approval of factory production control,

In accordance with the provisions laid down in the "Control Plan" of 11.2.14 relating to the European Technical Assessment 14/0381

The approved body shall retain the essential points of its actions referred to above and state the results obtained and conclusions drawn in a written report.

The approved certification body involved by the manufacturer shall issue an EC certificate of conformity of the product stating the conformity with the provisions of this European technical assessment.

In cases where the provisions of the European technical assessment and its "Control Plan" are no longer fulfilled the certification body shall withdraw the certificate of conformity and inform the Warrington Certification Limited without delay.



Signatories



Responsible Officer

C. Abbott* - Principal Certification Engineer



Approved

A. Kearns* - Technical Manager

* For and on behalf of Warrington Certification Limited.



Annex A

Reference Documents and LIST OF ABBREVIATIONS

References to standards mentioned in the ETA:

EN 13501-1	Fire classification of construction products and building elements – Part 1: Classification using test data from reaction to fire tests
EN 13501-2	Fire classification of construction products and building elements – Part 2: Classification using test data from fire resistance tests

Other reference documents:

EOTA TR 024	Characterisation, Aspects of Durability and Factory Production Control for Reactive Materials, Components and Products
ETAG No. 026: Part 2	Guideline For European Technical Approval of Fire Stopping and Fire Sealing Products, Part 3: Penetration Seals (used as European Assessment Document, EAD)



Annex B

Description of Product and Product Literature

fischer FiGM PFS+ Intumescent Sealant

A detailed specification of the product is contained in document "Evaluation Report" relating to the European Technical Approval ETA – 14/0381 issued on 7/10/14, of fischer FiGM PFS+ Intumescent Mastic which is a non-public part of this ETA.




Graphite mastic - FiGM-PFS+

A versatile, powerful, graphite based product that expands to 20 times its own volume

FireStop Product Range



Services - Dry Wall



Mixed Services - Masonry

BUILDING MATERIALS

Suitable for:

- Dry wall
- Masonry wall
- Concrete wall

STANDARDS & APPROVALS

British Standard
EN 1366-3: 2009

BS EN 1026



Approved
CP 5151

Not For use on Non-Masonry

ADVANTAGES

- Approved for a wide range of applications, many of which **do not require backing material**.
- Quicker and more economical than collars for many pipe applications.
- Tested in full scale drywall
- Both fire integrity and insulation ratings maintained due to stability of the highly insulative char.
- Tested with PVC, HDPE and ABS as well as insulated pipes.
- Easy clean up with water
- Odourless and paintable once cured.
- Tested with PVC Pipes up to 125mm diameter.

APPLICATIONS

- A wide range of service penetrations including pipes passing through dry and masonry walls.

DESCRIPTION

fischer FiGM-PFS+ is a powerful graphite based product which when exposed to fire expands up to 20 times its own volume; crushing through services as they melt to form a resilient fire seal.

Tested to BS EN1366-3, it is suitable for use within both drywall constructions and solid concrete or masonry walls, providing up to 2 hours fire and insulation ratings for most applications. These include plastic pipes (PVC, HDPE, ABS) up to 125mm diameter, insulated pipes, metal pipes, single and bunched cables plus mixed pipe and cable penetrations.

FiGM-PFS+ has excellent non slump properties coupled with ease of application due to its water based nature. Once cured, as well as being smoke, gas and water tight, it can also be painted.

BACKING MATERIALS

- For metal pipe applications mineral wool (min 80kg/m³) should be used.
- For most other tested applications, no backing material is required.
- Where increased insulation and/or acoustic performance is required; or to control sealant depth, use fischer FireStop foam, fischer B2 foam or mineral wool.

STORAGE

- FiGM-PFS+ should ideally be stored between +5°C and +25°C, indoors, above ground level in dry well ventilated conditions, in unopened and original packaging.
- Dispose of waste in accordance with local authority regulations.

INSTALLATION GUIDANCE







- Ensure the opening and any substrate which the product will come into contact with is clean, free from dust and loose particles.
- Ensure that all services are adequately supported so as to not exert movement that might disrupt the seal during a fire.
- Backing material, where required, should be installed centrally within the penetration.
- Sealant should be applied around the service(s) on both exposed faces.
- The sealant can be tooled and smoothed with a pallet knife using water
- All dimensions and tolerances should be in line with the sealant recommended guidelines as dictated by the relevant test data and/or assessments.



Annex C

Resistance to Fire Classification of fischer FiGM PFS+ Intumescent Mastic

C.1.1 Flexible and Rigid wall constructions according to 1.2.1 with wall thickness of minimum 120 mm

C.1.2 Penetration seal with fischer FiGM PFS+ Intumescent Mastic – Plastic Pipes

Construction details:

- fischer FiGM PFS+ Intumescent Mastic applied into the annular space to the required depth as per table C1.3

C.1.3

Penetration Specification	fischer FiGM PFS+ Intumescent Mastic (installed both faces)	Backing Material	Classification
PVC Pipe 40mm \varnothing 1.9-3mm wall thickness	10mm annulus x 25mm deep	N/A	EI120 U/C
PVC Pipe 125mm \varnothing 4.8-7.4mm wall thickness	16mm annulus x 25mm deep	30mm deep, 80Kg/m ³	EI120 U/C
HDPE Pipe 63mm \varnothing 7.2mm wall thickness, Cables up to 21mm \varnothing	300mm wide x 100mm high x 25mm deep	N/A	EI120 U/C
HDPE Pipe 90mm \varnothing 9.2mm wall thickness,	12.5mm annulus x 25mm deep	N/A	EI120 U/C
ABS Pipe 90mm \varnothing 6mm wall thickness,	12.5mm annulus x 25mm deep	N/A	EI120 U/C



C2.1 Flexible and Rigid wall constructions according to 1.2.1 with wall thickness of minimum 120 mm

C.2.2 Penetration seal with fischer FiGM PFS+ Intumescent Mastic – Insulated Metallic Pipes

- fischer FiGM PFS+ Intumescent Mastic applied into the annular space to the required depth as per table C2.3

C.2.3

Penetration Specification	fischer FiGM PFS+ Intumescent Mastic (installed both faces)	Backing Material	Classification
Copper/Steel Pipe 60mm \varnothing 0.8mm -14.2mm wall thickness, insulated with 32mm 'Armaflex AF' (CS) Continued Sustained	20mm annulus x 25mm deep	N/A	E120 U/C EI90 U/C
Copper/Steel Pipe 15mm \varnothing 0.8mm -7mm wall thickness, insulated with 13mm 'Armaflex AF' (CS) Continued Sustained	15mm annulus x 25mm deep	N/A	EI120 U/C



C3.1 Flexible and Rigid wall constructions according to 1.2.1 with wall thickness of minimum 100 mm

C3.2 Penetration seal with fischer FiGM PFS+ Intumescent Mastic – Plastic Pipes

Construction details:

- fischer FiGM PFS+ Intumescent Mastic applied into the annular space to the required depth as per table C1.3


C3.3

Penetration Specification	fischer FiGM PFS+ Intumescent Mastic (installed both faces)	Backing Material	Classification
PVC Pipe 40mm ø 1.9mm wall thickness	20mm annulus x 25mm deep	N/A	EI120 C/U
PVC Pipe 125mm ø 9.2mm wall thickness	20mm annulus x 25mm deep	N/A	EI60 C/U
ABS Pipe 40mm ø 1.9mm wall thickness	20mm annulus x 25mm deep	N/A	EI120 C/U
HDPP Pipe 40mmø 2mm wall thickness	20mm annulus x 25mm deep	N/A	EI120 C/U



C4.1 Flexible and Rigid wall constructions according to 1.2.1 with wall thickness of minimum 100 mm

C4.2 Penetration seal with fischer FiGM PFS+ Intumescent Mastic – Plastic Pipes



C4.3

Penetration Specification	fischer FiGM PFS+ Intumescent Mastic (installed both faces)	Backing Material	Classification
Copper/Steel Pipe 40mm ø 1.5mm – 14.2mm wall thickness insulated with 32mm 'Armaflex AF' (LS 650mm) Local Sustained 650mm	20mm annulus x 25mm deep	N/A	E120 C/U EI30 C/U
Copper/Steel Pipe 40mm - 159mm ø 2.0 mm – 14.2mm wall thickness insulated with 32mm 'Armaflex AF' (LS 650mm) Local Sustained 650mm	20mm annulus x 25mm deep	N/A	E120 C/U EI30 C/U
Copper/Steel Pipe 159mm ø 2.0 mm – 14.2mm wall thickness insulated with 30mm x 80kg/m³ 'Pipelane' SGR glass wool tube (LS 650mm) Local Sustained 650mm	20mm annulus x 25mm deep	N/A	E120 C/U EI30 C/U

